


AD-A284 286



IN PAGE

OMB No. 0704-0188

1 to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and section of information. Send comments regarding this burden estimate or any other aspect of this collection of information, writers Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1024, Arlington, rwork Reduction Project (0704-0188), Washington, DC 20503

1. AGENCY USE ONLY	2. REPORT DATE Mar-93	3. REPORT TYPE AND DATES COVERED FINAL TECH. Feb 19, 1993 through Feb 18, 1994	
4. TITLE AND SUBTITLE Workshop on Intelligent Processing for MBE and MOCVD		5. FUNDING NUMBERS N00014-93-1-0354	
6. AUTHOR(S) Dr. George N. Maracas			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Arizona State University Electrical Engineering Department Box: 875706 Tempe, AZ 85287-5706		9. PERFORMING ORGANIZATION REPORT NUMBER DWD 1817	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Administered by..... ARPA Sciences Office 3701 N. Fairfax Dr. Arlington, VA 22203-1714 Office of Naval Research - Resident Representative University of New Mexico Bandelier Hall West, Room 111 Albuquerque, NM 87131-0001			
11. SUPPLEMENTARY NOTES			
12a. DISTRIBUTION/AVAILABILITY STATEMENT Available to the public		12b. DISTRIBUTION CODE This document has been approved for public release and sale; its distribution is unlimited.	
13. ABSTRACT (Maximum 200 words) The Workshop on Intelligent Processing for MBE and MOCVD was held in Santa Fe, New Mexico on January 27 & 28, 1993. It assembled approximately fifty(50) researchers in the field of advanced sensors and controls to address issues in realization of intelligent control of MBE and MOCVD for III-V and II-VI devices. The workshop consisted of open sessions and presentations from researchers in the field of growth, sensors and control theory. MBE and MOCVD, presently being the two primary epitaxial growth technologies for quantum structured devices, were discussed to identify issues and directions for sensor and control algorithm development toward the realization of future electronic and photonic devices. Issues discussed were the present status of growth technologies, sensors for in-situ diagnostics, algorithms for real time control and cost of sensor implementation. Possibilities for future intelligent epitaxial systems and the insertion of the sensor/control systems into the technology base were also considered. DTIC QUALITY INSPECTED 3			
14. SUBJECT TERMS Intelligent Processing for MBE and MOCVD		15. NUMBER OF PAGES 13	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL

Arizona State University

College of Engineering and Applied Sciences
Department of Electrical Engineering
Box 875706
Tempe Arizona 85287-5706

(602) 965-8654
FAX (602) 965-0775


August 24, 1994

Defence Technical Information Center
Building 5, Cameron Station
Alexandria, VA 22304-6145

RE: Grant #N00014-93-1-0354
Workshop on Intelligent Processing for MBE and MOCVD
Principal Investigator - George Maracas
Final Technical Report

It has come to our attention that you may not have a copy of the final report for grant #N00014-93-1-0354 titled "Workshop on Intelligent Processing for MBE and MOCVD" that was originally sent out at the end of March 1993. Attached is an additional copy for your records.

Sincerely,



Holly Jordan
Administrative Assistant/Maracas

Accession For	
NTIS	CRA&I <input checked="" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

94-29344



94 9 07 1 5 6

Final Report
for
Workshop on
Intelligent Processing for MBE and MOCVD

Hotel Santa Fe
Santa Fe, New Mexico

January 27-28, 1992

by

George N. Maracas
Arizona State University
Electrical Engineering Department
ERC 154
Tempe, AZ 85287-5706

Tel. (602) 965-2562

Fax (602) 965-8654

Abstract

The Workshop on Intelligent Processing for MBE and MOCVD was held at the Hotel Santa Fe, Santa Fe, NM on January 27&28, 1993. It assembled approximately fifty (50) researchers in the field of advanced sensors and controls to address issues in the realization of intelligent control of MBE and MOCVD for III-V and II-VI devices. Presented here is a summary of the technical program and discussions held during the workshop.

Introduction

It is generally agreed that compound semiconductor epitaxial growth technology has had a rapid development over the past twenty years. Advanced devices such as modulation doped field effect transistors (MODFETs), resonant tunneling transistors (RTTs), heterojunction bipolar transistors (HBTs), quantum well lasers, detectors and modulators have been realized and continue to be developed. While successes in these areas have achieved the present state of III-V technology, future generations of devices require even more control of critical dimensions and materials properties than is presently available.

A one and one-half day workshop was held to discuss these issues. The workshop consisted of open sessions and ten minute presentations from researchers in the field of growth, sensors and control theory. MBE and MOCVD, presently being the two primary epitaxial growth technologies for quantum structured devices, were discussed to identify issues and directions for sensor and control algorithm development toward the realization of future electronic and photonic devices. Issues discussed were the present status of growth technologies, sensors for in-situ diagnostics, algorithms for real time control and cost of sensor implementation. Possibilities for future intelligent epitaxial systems and the insertion of the sensor/control systems into the technology base were also considered.

Requirements for future electronics and photonics manufacturing

Jane Alexander (DARPA) opened the workshop with an overview of the requirements for future manufacturing systems. There is a strong sentiment in moving away from the ever-increasingly expensive silicon fabrication lines toward smaller (\$50M), flexible lines which can manufacture high-end products. Present fab line utilization is only approximately 35% and considerable amount of time is spent in inspection and cleaning. Cost will be the overriding factor in determining the success of any future fabrication technology.

Ray Balcerak (DARPA) then spoke specifically about infrared focal plane array project and the requirements for epitaxy of II-VI compounds required to realize their goals. One of the major problems in II-VI epitaxy is temperature control. He stressed that temperature measurement in MBE needs to be significantly improved. He recommends that models be developed that describe the growth process and that cost of any intelligent sensor be reduced to approximately \$10K.

Growth

The degree of growth process control depends on the nature of the growth mechanisms of a particular technology. For instance, in MBE (an unstable process)

several parameters (group III flux, group V flux and temperature) need control to realize reproducible, high quality structures. The process control surface can be considered sharp and thus requires active feedback to maintain process control. Atomic layer epitaxy (ALE), on the other hand is a self assembling process characterized by a flat control surface and thus does not require active control. MOCVD lies somewhere between the two because of its chemically assisted growth nature. It was generally agreed that the different epitaxial growth technologies will require different levels of control.

There are many variables in the growth of III-V and II-VI compounds by MBE and MOCVD. Measurable parameters can be grouped into three categories depending on their relationship to the desired target epitaxial structure. Different materials systems (e.g. AlGaAs and HgCdTe) will have different tolerances on the growth conditions (listed as tertiary variables) and thus sensors for these may require different sensitivity and accuracy.

The process variables for MBE and MOCVD were grouped in order of importance for controlling growth of currently popular heterojunction devices.

Primary variables:

Alloy composition
Thickness

Secondary variables:

Doping
Alloy ordering (including defects)
Interface properties (abruptness)
Chemical state of initial growth surface (substrate properties)

Tertiary variables:

Growth temperature
Ambient pressure, temperature
Precursor species and fluences (beam fluxes, gas flow rates and composition)

Sensors

Sensor requirements for integration into epitaxial process control

In order for an intelligent sensor to become successfully integrated into the III-V and II-VI MBE and MOCVD growth community, it must satisfy certain requirements. Some of the requirements that were discussed are listed below. Atomic layer epitaxy (ALE) was also discussed since, because of its self-limiting, single atomic layer nature, does not require in-situ growth control of thickness or composition. It was suggested that ALE could be used to obtain calibration samples for in-situ or ex-situ sensors. The in-situ diagnostics discussed here can also be applied to ALE.

Sensors should:

- provide information on the growing material or the sources in real time
- be adaptable to existing growth reactors
- not limit the reliability of the growth system
- not alter the growth process
- be easy to align or calibrate
- be compatible with substrate rotation

not significantly affect the cost of the total growth system (be inexpensive)

Depending on the application, the sensor should have the capability to:
operate intermittently to provide process calibration information

or

operate continuously for logging of process parameters or failure alert

A brief description of sensors that have, or possibly may be applied to in-situ epitaxial growth are presented here. The discussion is not comprehensive and only limited to sensors that were discussed at the workshop.

Thermocouples (TC)

This is the most commonly used temperature sensing device because of wide temperature range (typically 0°C to 1200°C) and its low cost (~\$1K). A junction between dissimilar metals produces a temperature dependent voltage which is converted to temperature from a calibration table. A (p-i-d) temperature controller produces feedback power to the control point. Accuracy limitations in epitaxial reactors (10°C - 200°C) are a result of TC placement far from the desired control surface (substrate).

Optical pyrometry

The black body radiation (at fairly high temperatures) of a material with a certain emissivity is measured by a photodetector. The choice of detected wavelength depends on the bandgap of the material to be measured. Temperatures above 450°C can be measured for III-Vs. Multiple wavelength pyrometry increases the accuracy of temperature determination and it was shown that, in II-VIs, temperature control of $\pm 1^\circ\text{C}$ was possible. The cost of a multiple wavelength system is \$20K - \$22K while a single wavelength unit is approximately \$5K.

Projection Moiré thermometry

A diffraction grating (e.g. 1 μm pitch, L=3mm) is etched into the surface of a substrate of which temperature is to be measured. The amount of wafer expansion (a priori knowledge of the thermal expansion coefficient of material is required) is proportional to the temperature. The optical collection system consists of a beam splitter, lens and CCD camera to observe the Moiré fringes produced by the first order grating diffraction. The lens performs an optical 2D FFT which produces two spots on the CCD camera. The distance between the spots is proportional to the grating size change and thus the temperature. Temperature resolution is less than 1°C and cost is approximately \$10K.

Energy dispersive x-ray (EDX)

X-rays induced by an incident electron beam can be used to determine the chemical composition of a material. It was proposed that glancing angle EDX could be used in an MBE system to monitor surface lattice constant and composition. The cost of such a system would be approximately \$75K.

Reflection high energy electron diffraction (RHEED)

Diffraction of an electron beam (~10keV) from a crystalline surface onto a phosphorescent screen enables the measurement of surface reconstruction and lattice constant. This is commonly used in ultrahigh vacuum (UHV) reactors (standard equipment on MBE machines) to monitor growth rate and V/III ratio, for example. Growth rates are measured in a layer-by-layer growth mode by observing the intensity variation of a diffracted spot (RHEED oscillations). Using a video camera and

synchronizing pattern acquisition with substrate rotation enables surface structure monitoring under substrate rotation. Cross-sectional analysis of streaks can extract surface step distributions. The cost of a RHEED system is approximately \$20K-\$30K plus cost of any video image acquisition equipment.

Optical reflectance

Optical radiation at normal incidence is reflected from the growth surface and detected versus time. Assuming that the optical thickness or optical constants are known versus wavelength, alloy composition, growth rate or thickness can be measured. This has been extended to the growth of microcavity optical devices such as vertical cavity surface emitting lasers (VCSELs) where the Fabry-Perot cavity thickness is adjusted after growth interruption. A basic, one wavelength (HeNe laser) system is \$5K.

Reflectance difference spectroscopy (RDS)

A variation on the optical reflectance technique takes the difference in polarization induced by surface dipoles (for instance) to obtain chemical information of the surface and growth rate. Polarizers and synchronous detection instrumentation are required. The cost is approximately \$30K-40K.

Spectroscopic ellipsometry (SE)

The polarization of light reflected from a surface is analyzed as a function of wavelength. The response is fitted to (predetermined) optical constants of the material and a specific layer structure to extract alloy composition, thickness, growth rate and temperature. Two main types of ellipsometers were discussed: photelastic modulator SE and rotating analyzer SE. SE development is still continuing which is producing commercially available systems costing between \$15K and \$150K.

Infrared transmission/absorption

The temperature dependence of a semiconductor bandgap edge can be used to extract the substrate temperature in MBE and MOCVD. The band edge is determined spectroscopically in the temperature range $100^{\circ}\text{C} < T < 800^{\circ}\text{C}$. The position of the band edge can be obtained more accurately by differentiating the absorption spectrum and accuracy of $\pm 2^{\circ}\text{C}$ has been stated. Limitations are on thick, absorbing multilayer structures. The cost of a commercially available system (Intevac) is \$42K.

Ultrasonic gas flow sensing

Accurate determination of gas flows in MOCVD source lines can be obtained by measuring the acoustic velocity of the gases. A commercially available system (Epison) provides a gas velocity signal which has been used to control composition in MOCVD to 0.25%. The units cost \$5K per gas line. Multiplexing one unit among four lines has been demonstrated.

Ultraviolet (UV) absorption and fluorescence

The fluorescence and absorption spectra of excited molecules can be used to identify chemical species and their concentrations. UV lamp excitation is used for absorption and tunable lasers for fluorescence while dispersive optics are used for detection. These techniques can be used near the growth surface or near the sources to obtain information in the gaseous state. An absorption/fluorescence system has been built which can be fitted to existing MBE systems without modifying the growth chamber (Martin Marietta). This system uses light conduits to bring the light parallel to the substrate surface. Typical costs of basic systems is ~\$10K-20K.

Second harmonic generation (SHG)

Laser pulses are incident onto the surface of a semiconductor. The discontinuity in the potential at the interface generates a second harmonic of the incident radiation which is detectable by standard optical techniques. This second harmonic light is surface reconstruction sensitive. The cost of such an instrument is approximately \$50K.

Sensor	measurable param	accuracy/sensi.	cost
Thermocouple	T	10 - 200°C	\$1K
Optical pyrometer (multi λ)	T	$\pm 1^\circ\text{C}$	\$20K-22K
Projection Moiré	T	$<1^\circ\text{C}$	\$10K
X-ray diffraction	t	$<1\%$	\$120K
EDX	surface composition	-	\$75K
RHEED	R_g , surf. reconstr.	$\sim 5\%$	\$20-\$30K
Spectroscopic ellipsometry	t, x, T, Refl.	few %	\$10 - 150K
Optical reflectance	t, x		\$5K
Reflectance difference spectr.	surf. chemistry		\$30K-40K
IR transmission/absorption $\Rightarrow E_g$	T	$\pm 2^\circ\text{C}$	\$42K
Ultrasonic gas flow sensing	gas flow	$\pm 0.25\%$	\$15K (X4)
UV absorption and fluorescence	chem. species		\$10K-20K
Second harmonic generation	surf.state, R_g		\$ 50K

Algorithms/control

Efficient analysis and control algorithms need to be developed toward the goal of attaining intelligent processes which will reliably produce target epitaxial structures. This may require concurrent development of growth models and their coupling to sensor models. Several talks on real time parameter tracking and control were presented which addressed possible directions and approaches.

Two approaches are possible when analyzing the growth of a complicated multilayer structure. One is to use all the information gained during the entire growth (history dependent) and the other is to use only the information obtained in the changing surface (history independent). The latter technique has been used to achieve control of the near-surface MBE AlGaAs composition by SE on extremely small structures such as quantum wells. The prior technique is more appropriate for VCSEL mirror structures since the optically active region is several quarter wavelengths of light thick.

Tracking of parameters such as MBE growth rate by SE require algorithms that can adapt to changes in related parameters such as temperature as the optical constants drift with temperature. Incomplete data problem algorithms have been successfully used to track growth rate in the presence of varying temperature and surface roughness.

Model based control and sensing has been used in MOCVD by extended Kalman Filtering techniques. A suggestion was to couple sensor models with growth models. Calibration of growth models still needs to be achieved. The number of variables required for some detailed growth models is large. Calibration could require monitoring all aspects of growth which could easily create unmanageably large quantities of data.

It was suggested that describing a complex system such as an MBE requires a nonlinear dynamical system model. Specifically, a decentralized, hierarchical control strategy, including adaptation should be necessary to attain control. A requirement on the sensor response is that the system parameters be sampled five times faster than the response time of the MBE system.

On the subject of system response, an effusion cell flux transient was modeled toward the goal of reducing the transient. The response was approximated by a simple transform in attempts to minimize state information for the cell.

Another approach to the intelligent processing problem involved applying neural networks. There were no presentations on this subject.

Other issues:

Three other issues were mentioned but, due to time constraints, were not discussed in detail. They are briefly described here and would be appropriate to address more completely in a future workshop.

Is it feasible to have one epitaxial reactor grow all (device) structures?

Such a reactor might be complex, versatile and capable of several in-situ controls. Some discussion ensued about the possibly high cost of such a system in comparison to a dedicated "single-structure" system.

III-V sensor development should be transferable to silicon processes.

This discussion was motivated by the large portion of the semiconductor market presently held by the silicon industry in comparison to compound semiconductors. Epitaxy of III-Vs and II-VIs is more difficult than that of silicon so sensors should be easily adaptable to silicon processes. The evolution of SiGe has put the silicon industry into the compound semiconductor field. Therefore, materials technologies developed for III-Vs and II-VIs could be adapted to SiGe. Such a connection might spur the silicon industry to fund advanced sensor and process control development for non-Si based compounds.

To what extent should detailed growth models be developed?

This question came up because there was very little discussion on first-principles growth models. One view was that efficient development of a growth technology could not occur without deep physical insight into the process. It was generally agreed that some physical models must be available for this purpose and for analyzing situations where the process mysteriously fails to meet specifications. The extent of the required physical model depth was mentioned but not discussed in detail due to time limitations.

Final statements

The Intelligent Processing Workshop spurred a considerable amount of discussion on sensor, analysis and control algorithm and materials growth issues. Comments from the participants, during and after the workshop, were generally positive and there was much interest in holding future workshops. Many constructive and useful suggestions were made on improving the organization and exchange of ideas. These will be implemented if future workshops occur.

Program**Workshop on Intelligent Processing for MBE and MOCVD**

January 27 & 28, 1993

Hotel Santa Fe Santa Fe, NM

PROGRAM

Wednesday, January 27, 1993

8:00 - 9:00 Continental breakfast**9:00 - 9:15**George Maracas (ASU) Introduction, purpose of meeting**9:15 - 10:00**Jane Alexander (DARPA) Manufacturing directions for future electronics and photonics**10:00- 10:40****Growth - George Maracas**Salah M. Bedair (NCSU)

Film Thickness and Composition Control by ALE Growth

Andrew Purdes (TI)

Sensor-Based MBE - Promise and Limitations

Dick Shealy (Cornell)

Real Time Control of Advanced OMVPE Processes

Ronald Gale (Kopin)

Intelligent Processing of Epitaxial Materials using MOCVD materials

10:40 -11:00**Coffee break****11:00- 12:10****Growth (cont.) - Manijeh Razeghi**John Dinan (USNVL)

Issues for real-time control of MBE of HgCdTe

John Jensen (Hughes)

HRL activities related to MBE/MOMBE of III-V and II-VI

SensorsDoug Collins (CalTech)

Applying RHEED to MBE Process Control

Haluk Sankur (Rockwell)

Laser Reflectance as an in situ monitor for MOCVD of III-V epilayers

Paul Luscher (Intevac)

Accurate, real-time substrate temperature measurement control

Colin Wood (U. MD)

Real-time surface composition control by energy dispersive x-ray analysis

12:15 - 1:30**Lunch****1:30 - 2:30****Sensors - Andrew Purdes**Walter Duncan (TI)

High-speed Spectral Ellipsometry for In-Situ Diagnostics and Control

John Woollam (U.Nebr.)

Design and Performance of a Low Cost Multiple

Wavelength in situ Ellipsometer

George Maracas (ASU)

Spectroscopic ellipsometry for III-V MBE

Manijeh Razeghi (NW U.)

In Situ Investigation of MOCVD Deposition of

Semiconductors by RDS

Jeff Tsao (Sandia)

VCSEL growth by reflectance feedback

Ken Bacher (Stanford)

In-situ corrections to vertical cavity optical devices grown by MBE

2:30 - 2:50**Coffee break****2:50 - 3:50****Sensors (cont.) - Salah Bedair**Steven DenBaars (UCSB)

Composition control of epitaxial films by real time ultrasonic sensing of metalorganic vapor concentration variations

<u>Steve Brueck</u> (U. NM)	Real-time temp. measurement using projection Moiré techniques
<u>Glenn Westphal</u> (TI)	Multi- λ pyrometry for II-VIs on MBE
<u>Tom Pearsall</u> (U. Wash.)	In-situ monitoring of epitaxial growth using UV absorption and fluorescence spectroscopies
<u>Stefan Svensson</u> (Mart.Mar)	Optical beam flux monitoring for MBE
<u>Stuart Irvine</u> (Rockwell)	Integrated in-situ monitoring for II-VI MOVPE
3:50 - 4:40	Discussion - Bob Trew
4:40 - 5:00	Nanofabrication Network - Jane Alexander

Dinner - everyone for themselves

Thursday, January 28, 1993

8:00 - 9:00 Continental breakfast

9:00 - 9:30 Discussion #1 - recap of previous day - Maracas

9:30 - 10:20 Algorithms - Walter Duncan

Dave Aspnes (NCSU) A History-Independent Algorithm for Determining Outer-Layer Dielectric Responses from Ellips. Data: Application to Closed-Loop Feedback Control of AlGaAs Epitaxy

Guy R.L. Sohie (GE) New algorithms for dynamic tracking of temperature and growth parameters in MBE ellipsometry

Ted Schulman (ISI) Model-based sensing and control for MOCVD

Kostas Tsakalis (ASU) Control of MBE by spectroscopic ellipsometry

Jim Vlcek (EPI) Effusion cell flux transient compensation

10:20 - 10:40 Coffee break

10:45-12:15 Discussion #2 - directions - Dave Aspnes

What are the variables that need to be controlled?

What variables can be measured and controlled? What tolerances are required?

Which variables are presently under control and which need improved control?

What sensor control technologies presently are being used?

What are the algorithmic speed requirements for real time control?

What sensors and controls can reasonably be developed? (the big payoff)

Which sensors have a near term market?

Where do we go from here?

12:15 Lunch and adjournment

NOTE:

Presentations are 10 minutes long including questions.
Please be prepared to discuss the questions listed in the discussion sessions (this includes attendees not giving presentations).

Attire is casual.

Attendee List

Jane. A. Alexander
DARPA/MTO
3701 N. Fairfax Dr.
Arlington, VA 22203-1714
Tel. (703)696-2233
Fax: (703)696-2201
jalexander@DARPA.MIL

Dave Aspnes
NCSU
Physics Dept.
Raleigh, NC 27651
Tel. (919)515-4261
Fax: (919)515-6538
aspnes@pyvax.physics.ncsu.edu

Ken Bacher
Stanford University
Electrical Engineering, Solid State Lab
McCullough 226
Stanford, CA 94305-4055
Tel. (415)723-8040
Fax: (415)723-4659
bacher@luciano.stanford.edu

Salah Bedair
NCSU
EE Dept., Daniels Hall
P.O. Box 7911
Raleigh, NC 27695-7911
Tel. (919)515-5204
Fax: (919)515-3027
mlb@ecegrad.ncsu.edu

Raymond Balcerak
DARPA/MTO
3701 N. Fairfax Dr.
Arlington, VA 22203-1714
Tel. (703)696-2277
Fax: (703)696-2201
rbalcerak@darpa.mil

William G. Barker
DARPA/DSO
3701 N. Fairfax Dr.
Arlington, VA 22203-1714
Tel. (703)696-2281
Fax: (703)696-2201
wbarker@darpa.mil

William Breiland
Sandia National Labs
Dept. 1126
Albuquerque, NM 87185-5800
Tel. (505)844-7029
Fax: (505)844-3211

Steve Brueck
U. New Mexico
Center For High Technology
Albuquerque, NM 87131
Tel. (505)277-3317
Fax:

Doug Collins
CalTech
MS 128-95
Pasadena, CA 91125
Tel. (818)356-4786
Fax: (818)356-4817
dac@ssdp.caltech.edu

Steve DenBaars
UCSB
Materials Department
Santa Barbara, CA 93106
Tel. (805)893-8511
Fax: (805)893-8502
denbaars@engrhub.ucsb.edu

Roger DeWames
Rockwell Int'l Science Center
1049 Camino Dos Rios
Thousand Oaks, CA 91360
Tel. (805)373-4183
Fax: (805)373-4719

John Dinan
US Army Night Vision & Electro-Optics
Directorate
Director
AMSEL-RD-NV-LD-FP (Dinan)
Ft. Belvoir, VA 22060
Tel. (703)704-3234
Fax: (703)704-3246
dinan@nvl.army.mil

Walter Duncan
Texas Instruments
P.O. Box 655936 MS 147
Dallas, TX 75265
Tel. (214)995-3134
Fax: (214)
995-7785
duncan@resbld.csc.ti.com

Ron Gale
Kopin
695 Myles Standish Blvd.
Tauton, MA 02780
Tel. (508)824-6696
Fax: (508)822-1381

James Hwang
Lehigh University
161 Memorial Dr. E
Rm 161
Bethlehem, PA 18015-3084
Tel. (215)758-5104
Fax: (215)758-5941
JH00@lehigh.edu

Stuart Irvine
Rockwell International Science Center
1049 Camino Dos Rios
Thousand Oaks, CA 91360
Tel. (805)373-4484
Fax:

John Jensen
Hughes Research Lab
3011 Malibu Canyon Rd. RL92
Malibu, CA 90265
Tel. (310)317-5388
Fax: (310)317-5483
0082679@msgate.emis.hac.com

Nasser Karam
Spire Corporation
One Patriots Park
Bedford, MA 01730
Tel. (617)275-6000
Fax: (617)275-7470

Robert Kee
Sandia National Labs
Computational Mechanics Dept.
Livermore, CA 94551
Tel. (510)294-3272
Fax: (510)294-1459

Kevin Killeen
Sandia National Labs
Dept. 1126
Albuquerque, NM 87185-5800
Tel. (505)844-5164
Fax: (505)844-3211

Carol J. Kramer
DARPA/MTO
3701 N. Fairfax Dr.
Arlington, VA 22203-1714
Tel. (703)696-2274
Fax: (703)696-2201
carolkramer:mto:darpa

George Maracas
Arizona State University
Engineering Research Center
Tempe, AZ 85287-5706
Tel. (602)965-2562
Fax: (602)965-0775
maracas@asuvas.eas.asu.edu

Andy Purdes
Texas Instruments
P.O. Box 655936 MS 147
Dallas TX 75265
Tel. (214)995-5559
Fax: (214)995-7785
purdes@resbld.csc.ti.com

T. P. Pearsall
University of Washington
FT-10
Seattle, WA 98195
Tel. (206)543-3063
543-4109
Fax: (206)
543-3100
543-3842
pearsall@maxwell.ee.washington.edu

Mamijeh Razeghi
Northwestern U
E & CE Dept.
Evanston, IL 60208-3118
Tel. (708)491-7251
Fax: (708)467-1817

John Roth
Hughes Research
3001 Malibu Canyon Rd.
Malibu, CA 90265
Tel.
Fax:

Linton Salmon
NSF
RM 1151
1800 G Street NW
Washington, DC 20550
Tel. (202)357-9618
Fax:
lsalmon@nsf.gov

Guy R.L. Sohie
GE/CRD
Building KW Room C603
P.O. Box 8
Schenectady, NY 12301
Tel. (518)387-5692
Fax: (518)387-7332
sohie@manowar.crd.ge.com

Haluk Sankur
Rockwell
083-A20
P.O. Box 1085
Thousand Oaks, CA 91358
Tel. (805)373-4263
Fax:

James Shealy
Cornell
311 Phillips Hall
School of EE
Ithaca, NY 14853
Tel. (607)255-4657
Fax: (607)254-4565

Richard Singer
Institute for Defense Analyses
1801 N. Beauregard St.
Alexandria, VA 22311-1772
Tel. (703)845-6764
Fax: (703)578-2877

Ted Schulman
Integrated Systems Inc.
3260 Jay Street
Santa Clara, CA 95054
Tel. (408)980-1500
Fax: (408)980-0400
tschulman@ISI.COM

Frank Smith
Loral
2 Forbes Rd.
Lexington, MA 02173
Tel. (617)863-4079
Fax: (617)863-3638

Stefan Svensson
Martin Marietta Labs
1450 S. Rolling Rd.
Baltimore, MD 21227
Tel. (410)204-2649
Fax: (410)204-2100
svensson@mml.mmc.com

Bob Trew
Electronics Division
U.S. Army Research Office
P.O. Box 12211
Research Triangle, NC 27709
Tel. (919)549-4243
Fax: (919)549-4310
trew@aro-emh1.army.mil

Jeff Tsao
Sandia National Labs
Dept. 1311
Albuquerque, NM 87185-5800
Tel. (505)844-7092
Fax: (505)844-8985
jytsao@sandia.gov

Glenn Westphal
Texas Instruments
P.O. Box 655936
MS/154
Dallas, TX 75265
Tel. (214)995-4054
Fax: (214) 995-6558
westphal@resbld.css.ti.com

John Woollam
J. A. Woollam Co.
650 J Street, Suite 39
Lincoln, NE 68508
Tel. (402)477-7501
Fax: (402)
477-8214

Colin Wood
U of Maryland
Lab for Phys. Sci.
4928 College Ave
College Park, MD 20742
Tel. (301)277-4190
Fax: (301)2776580

Barbara Yoon
DARPA/MTO
3701 N. Fairfax Dr.
Arlington, VA 22203-1714
Tel. (703)696-2234
Fax: (703)696-2201
BYOON@DARPA.MIL

James Vichek
300 E. 4th st Apt. 512
St. Paul, MN 55101
Tel.
Fax:

David Kopchek
University of New Mexico
Center for High Technology Materials
CHIM,EECE Building, Rm 125
Albuquerque, NM 87131-0681
Tel. (505)277-0612
Fax: (505)277-0614
kopchik@chtm.eece.unm.edu

Kostas Tsakalis
Arizona State University
Electrical Engineering Dept
Tempe, AZ 85287-5706
Tel. (602) 965-3424
Fax: